


## Electrically Insulating, High Performance, Thermally Conductive Phase Change Material

### Features and Benefits

- Thermal impedance: 0.18°C-in<sup>2</sup>/W (@25 psi)
- Natural tack for ease of assembly
- Exceptional thermal performance in an insulated pad



Hi-Flow 330P is a thermally conductive phase change material featuring a natural tack on one side and reinforced with a polyimide film. The polyimide film provides a high dielectric strength and cut-through resistance. Hi-Flow 330P offers excellent handling and consistent liner peel-off characteristics. The material is designed for use between a high power electrical device requiring electrical isolation and its heat sink. Bergquist recommends the use clips or springs for phase change materials to assure constant pressure between the component interface and the heat sink.

### Typical Applications

- Spring / clip-mounted devices
- Discrete power semiconductors and modules


### Configurations Available

- Roll form, die-cut parts, sheet form
- Available with 1.0 mil (Hi-Flow 330P1.0), 1.5 mil (Hi-Flow 330P1.5) or 2.0 mil (Hi-Flow 330P2.0) Polyimide reinforcement carrier

TYPICAL PROPERTIES OF HI-FLOW 330P						
PROPERTY	IMPERIAL VALUE	METRIC VALUE	TEST METHOD			
Color	Gold	Gold	Visual			
Reinforcement Carrier	Polyimide	Polyimide	—			
Thickness (inch) / (mm)	0.0045 - 0.0055	0.114 - 0.140	—			
Film Thickness (inch) / (mm)	0.001 - 0.002	0.025 - 0.050	ASTM D374			
Inherent Surface Tack (1 or 2-Side)	1	1	—			
Elongation (%)	40	40	ASTM D882A			
Tensile Strength (psi)	7000	7000	ASTM D882A			
Continuous Use Temp (°F / °C)	-40 to 257	-40 to 125	—			
Phase Change Softening Temp (°F / °C)	126	52	ASTM D3418			
ELECTRICAL						
Dielectric Breakdown Voltage (Vac)	5000	5000	ASTM D149			
Dielectric Constant (1000 Hz)	4.5	4.5	ASTM D150			
Volume Resistivity (Ohm-meter)	10 <sup>12</sup>	10 <sup>12</sup>	ASTM D257			
Flame Rating	V-O	V-O	U.L. 94			
THERMAL						
Thermal Conductivity (W/m-K)(1)	1.4	1.4	ASTM D5470			
THERMAL PERFORMANCE vs PRESSURE						
	Pressure (psi)	10	25	50	100	200
TO-220 Thermal Performance (°C/W) 0.0010"		1.22	1.17	1.13	1.10	1.08
TO-220 Thermal Performance (°C/W) 0.0015"		1.44	1.40	1.38	1.35	1.33
TO-220 Thermal Performance (°C/W) 0.0020"		1.67	1.63	1.60	1.58	1.54
Thermal Impedance (°C-in <sup>2</sup> /W)(2) 0.0010"		0.19	0.18	0.17	0.16	0.15
Thermal Impedance (°C-in <sup>2</sup> /W)(2) 0.0015"		0.21	0.21	0.21	0.19	0.18
Thermal Impedance (°C-in <sup>2</sup> /W)(2) 0.0020"		0.26	0.26	0.24	0.23	0.22

1) This is the measured thermal conductivity of the Hi-Flow wax coating. It represents one conducting layer in a three-layer laminate. The Hi-Flow coatings are phase change compounds. These layers will respond to heat and pressure induced stresses. The overall conductivity of the material in post-phase change, thin film products is highly dependent upon the heat and pressure applied. This characteristic is not accounted for in ASTM D5470. Please contact Bergquist Product Management if additional specifications are required.  
2) The ASTM D5470 test fixture was used and the test sample was conditioned at 70°C prior to test. The recorded value includes interfacial thermal resistance. These values are provided for reference only. Actual application performance is directly related to the surface roughness, flatness and pressure applied.

### Building a Part Number



### Standard Options

◀ example  
 NA = Selected standard option. If not selecting a standard option, insert company name, drawing number, and revision level.  
 \_\_\_ = Standard configuration dash number, 1112 = 11" x 12" sheets, 11/250 = 11" x 250' rolls, or 00 = custom configuration  
 01 = Natural Tack  
 Standard Polyimide Thickness Available = 0.001", 0.0015", 0.002"  
 HF330P = Hi-Flow 330P Phase Change Material

Note: To build a part number, visit our website at [www.bergquistcompany.com](http://www.bergquistcompany.com).

Hi-Flow®: U.S. Patent 6,197,859 and others



[www.bergquistcompany.com](http://www.bergquistcompany.com)

The Bergquist Company - North American Headquarters  
 18930 West 78th Street  
 Chanhassen, MN 55317  
 Phone: 800-347-4572  
 Fax: 952-835-0430

The Bergquist Company - European Headquarters  
 Bramenberg 9a, 3755 BT Eemnes  
 Netherlands  
 Phone: 31-35-5380684  
 Fax: 31-35-5380295

The Bergquist Company - Asia  
 Room 15, 8/F Wah Wai Industrial Centre  
 No. 38-40, Au Pui Wan Street  
 Fotan, Shatin, N.T. Hong Kong  
 Ph: 852.2690.9296  
 Fax: 852.2690.2344

All statements, technical information and recommendations herein are based on tests we believe to be reliable, and THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MARKETABILITY AND FITNESS FOR PURPOSE. Sellers and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and the user assumes all risks and liability whatsoever in connection therewith. NEITHER SELLER NOR MANUFACTURER SHALL BE LIABLE EITHER IN TORT OR IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL OR CONSEQUENTIAL INCLUDING LOSS OF PROFITS OR REVENUE ARISING OUT OF THE USE OR THE INABILITY TO USE A PRODUCT. No statement, purchase order or recommendations by seller or purchaser not contained herein shall have any force or effect unless in an agreement signed by the officers of the seller and manufacturer.  
 PDS\_HF330P\_0609